

TECHNICAL DATA SHEET

Panel Thickness	Standard	Unit	4mm
Weight		Kg/m ²	5.47
Tolerance in length	DIN 16927/ISO 11833-1	mm	-0/+3
Tolerance in width	DIN 16927/ISO 11833-1	mm	-0/+2
Tolerance in thickness	DIN 16927/ISO 11833-1	mm	±0.10
Horizontal flatness	DIN ISO 1101	mm	5
Longitudinal roughness	DIN ISO 1101	mm	5
Technical Properties			
Section Modulus W	DIN 53293	cm ³ /m	1.25
Rigidity (Poisson's ratio $\mu=0.3$) E.J	DIN 53293	kNm ² /m	0.14
Alloy	EN 573-3	ENAW	3003
Temper of Cover Sheets	EN 515		H14
Modulus of Elasticity	EN 1999 1-1	N/mm ²	70,000
0.2% Proof Stress	EN 485-2	N/mm ²	Rp0.2 ≥100
Elongation	EN 485-2	%	A50 ≥ 2
Surface			Coil Coating
Lacquering			(FEVE Finish)
Thickness of coating		um	>26
Gloss (initial value)	ASTM D523-14	%	36.3
Pencil Hardness	ASTM D3363-05		2H
Adhesion of Coating	ASTM D3359-09		5B
Coating Flexibility	ASTM D522/D522M-13		No visible crack
Detergent Resistance	ASTM D2248-01a		No visible change
Impact Resistance	ASTM D2794-93		>160 lb·inch
Peel Strength	ASTM D903-98		0.649 kgf/mm
Shear Strength	ASTM D732-10		26.6 Mpa
Tensile Strength of Aluminium	ASTM D638-14		48.2 Mpa
Chalking Test	ASTM D4214-07		No Chalking
Muriatic Acid Resistance	AAMA 2604-13		No blistering or other visual change
Mortar Resistance	AAMA 2604-13		No loss of adhesion or any other visual change
Thermal Conductivity	ASTM C518-15		0.128W/(m·K)
Coefficient of Linear Thermal Expansion	ASTM D696-2016		Average: 199.9x10 ⁻⁶
Acoustical Properties			
Sound Absorption Factor as	ISO 354		0.05
Sound Transmission Loss Rw	ISO 717-1	DB	25
Temperature Range		°C	-50--+80